



玖龙牌单面涂布白卡纸技术指标(销售)

Nine Dragons brand coated ivory board technical standard

检测项目		单位	检测方法	偏差	标准								
Items		Unit	Standards	Tolerance	Standard								
定量 Grammage		g/m²	GB/T451.2 ISO536	±3%	170	190	200	210	230	250	300	350	400
厚度 Thickness		µm	GB/T451.3 ISO534	-	205± 10	245± 10	265± 10	275± 10	310± 10	345± 12	415± 12	485± 15	555± 15
泰伯挺度 Taber Stiffness	CD	mN·m	GB/T22364 ISO2493	±15%	1.1	2	2.5	3	4	4.5	7	11	15
	MD	mN·m			2.1	4	5	6	8	9.5	15	23	28
水分 Moisture		%	GB/T462 ISO287	±1.5	7.5								
PPS 表面粗糙度 Surface Roughness		µm	GB/T22363 ISO8791	≤	1.5								
亮度 Brightness (D65)	Top	%	GB/T7974 ISO2470	±3	91								
	Back				87								
光泽度 75° Gloss-Top		%	GB/T8941 ISO8254	≥	43								
印刷表面强度 IGT-Picking-Top		m/s	GB/T22365 ISO3783	≥	1.3								
层间结合强度 Ply Bond		J/m²	GB26203 TAPPI569	≥	120								
表面吸水性 Cobb-Top(60s)		g/m²	GB/T1540 ISO535	≤	60								
偏斜度-平张 Squareness		mm	GB/T451.1 ISO287	-	0~2								
尺寸偏差 Size Deviation		mm		-	0~2								
检测条件 Testing Condition:													
温度 Temperature: (23±1) °C 相对湿度 Relative Humidity: (50±2) RH%													

玖龙纸业(东莞)有限公司
2024年9月24日